

Jabil PETg 0800 ESD Filament

Technical Data Sheet

Product Description

Jabil Engineered Materials PETg 0800 ESD is an easy processing, electrostatic dissipative (ESD) product for printing parts that require protection from electrostatic discharge. This product has high strength and stiffness with a good balance of properties in XY and Z directions and the added benefit of ESD for jigs, fixtures and tooling that needs to safely handle electronic components.



Advantages

Applications include jigs, fixtures and tooling, housings and components where permanent static dissipation is required. Produces tough parts with excellent surface quality and minimal warp.

Storage and Use

PETg is a hygroscopic material, meaning it will absorb moisture from the atmosphere, affecting visual quality and mechanical properties. For best results, print and store filament in a dry environment. If necessary, dry filament in an oven at 65 °C (150 °F) for 6 – 12 hours.

For the latest print profiles, search for Jabil Engineered Materials in the Cura Marketplace.

For complete copies of the Print Settings and the Printing & Drying Guide, visit our [PETg 0800 ESD Webpage](#).

Properties

Mechanical Properties			
	Test Condition	Typical Value	Method
Tensile Modulus (MPa)	XY coupons, Ambient	1895	ASTM D638, Type I
Tensile Elongation at Break (%)		7.9	
Ultimate Tensile Strength (MPa)		38.8	
Flexural Modulus (MPa)	XY coupons, Ambient	2050	ASTM D790
Flexural Strength (MPa)		71.6	
Izod Impact, notched (J/m)	XY coupons, Ambient	48.5	ASTM D256
Izod impact, un-notched (J/m)		415.9	

1. Testing conducted on coupons printed at a temperature of 270 °C, ±45° infill, 0.15 mm layer height and 3 wall contours. Typical values are for reference only.

Thermal Properties			
	Test Condition	Typical Value	Method
Heat Deflection Temperature (°C)	0.455 Mpa	67.4	DMA

1. Testing conducted on coupons printed at a temperature of 270 °C, ±45° infill, 0.15 mm layer height and 3 wall contours. Typical values are for reference only.

Other Physical Properties

	Test Condition	Typical Value	Method
Density (g/cm ³)	Ambient	1.26	ASTM D792
Surface Resistivity (ohm/sq)	Ambient	≤E9	ANSI/ESD STM11.11

Dimensional Properties

	Test Condition	Typical Value	Method
Diameter: Mean, Indiv. Axis (mm)	In-line, 100% inspection	1.75±0.05 2.85±0.05	Laser Micrometer

Disclaimer: The information in this technical data sheet, including material properties, are obtained from testing representative samples under carefully controlled conditions and are provided for reference only. Material properties may be impacted by storage, handling, processing equipment/parameters, and product design, among other factors. The information is not a substitute for user testing to determine fitness for any specific use and the user is responsible for ensuring safe and lawful use of the product.

No express or implied warranties are provided and the implied warranties of merchantability or fitness for a particular purpose are expressly disclaimed. No representations are made, and no liability is assumed arising from or relating to the product.

Copyright/Trademark: © 2020 Jabil Inc. All rights reserved. JABIL® and the JABIL logo are registered trademarks of Jabil Inc.